ILDYED FX3

(Fixing Agent for Direct Dyestuffs)

ILDYED FX3 is a special epoxy cationic resin. ILDYED FX3 is an excellent fixing agent for knit of T/C, cotton, and towel. ILDYED FX3 has an outstanding fixing effect and stability even though it is economical. And there is no possibility of air contamination since it has not CN-radical. That is, there is no harmful pollutant as formalin-drying done.

■ SPECIFICATIONS ■

- Appearance : Light yellowish transparent liquid

Chemical component : Special epoxy cationic resin
Solubility : Soluble in cold & hot water

- Ionicity : Cationic

- Active contents (%) : $48.0 \sim 52.0$ - pH (1% aq. Solution) : $4.0 \sim 6.0$

■ FEATURES ■

1. ILDYED FX3 increases washing and rubbing fastness without reduction of light fastness.

- 2. ILDYED FX3 is especially splendid for chlorine fastness.
- 3. ILDYED FX3 has no influence in textile touch after fixing treatment.
- 4. ILDYED FX3 minimizes change of color.
- With a small quantity, ILDYED FX3 furnishes good effect.(There may be a little effect on red and green by the depth of color)

■ APPLICATION

Dipping	2 ~ 3%(o.w.f)
Padding	0.5 ~ 1.5(o.w.f)
Time & Temperature	60°C × 10 ~ 20 min.

^{*} Dosage depends on the depth of color.

■ ELIMINATION OF ILDYED FX3 ■

1. Post-Fixing

 $\square\,\text{NaOH(Flake)} \qquad \qquad : 2\,\sim\,3\text{g/I}$

 $\Box H_2O_2(35\%)$: 5 ~ 10cc/l

□ ILTOL SH : $2 \sim 3g/I$

90 ~ 95 °C \times 30 ~ 60 min.

2. Elimination of Residual Peroxide

□ ILANTI OH : $2 \sim 3g/I$

50 ~ 60 °C \times 20 min.

■ PACKING UNIT ■

100kgs and 200kgs PVC Drum